

# AccuCast™ 77

## Integral Water Repellent Admixture for Concrete and Masonry Products

### DESCRIPTION:

**AccuCast™ 77** is a polymeric liquid water-repellent admixture that is part of a system of polymeric admixtures mixed throughout the concrete mix of normal, medium, lightweight concrete block, and ready mixed concrete.

**AccuCast™ 77** provides long-lasting resistance to water penetration by reacting to form a very effective water repellent network throughout masonry units and concrete. Polymeric admixtures are a proven technology and have earned a reputation for their ability to effectively prevent moisture from penetrating concrete masonry walls as well as concrete.

### APPLICATIONS:

**AccuCast™ 77** is an integral water-repellent admixture system for use in:

- Concrete block (normal, medium, and lightweight)
- Mortar
- Cast-in-place concrete
- Grout
- Paving stones
- Roofing tile
- Concrete brick
- Stucco

### ADVANTAGES:

- Less maintenance and moisture damage due to water repellency
- Inhibits water transmission through hardened cast-in-place concrete

### DOSAGE RATE:

**AccuCast™ 77** is recommended for use at the following dosages:

12-25 ozs./cwt.-*Normal Weight Concrete Block* (780-1630 mL/100kg)

18-28 ozs./cwt.-*Medium Weight Concrete Block* (1175-1825 mL/100kg)

25-36 ozs./cwt.-*Lightweight Concrete Block* (1630-2350 mL/100kg)

3-4 ozs./cwt.-*Ready-Mixed Concrete* (196-327 mL/100kg)

*Because local job conditions vary and optimum dosages need to be determined, contact your local Premiere Concrete Solutions Specialist for further assistance to ensure proper water repellent system performance.*

### SPECIFICATIONS:

Conforms to:

- ASTM E 514 Wind Driven Rain Resistance
- ASTM C 1072, ASTM E 72 Bond Strength To Mortar
- ASTM E 96 Reduced Water Vapor Transmission
- ASTM C 67, ASTM C 140, ASTM C 642 Reduced Absorption Rates
- ASTM C 140 Increased Compressive Strength



# AccuCast™ 77

## PRECAUTIONS:

**AccuCast™ 77** will not correct building design flaws, out of spec materials, mix proportion errors, incorrect manufacturing procedures, or unorthodox construction practices.

Proper block manufacturing procedures, mixing, and proportioning of mixes must be incorporated.

**Premiere Concrete Admixtures** cannot be responsible for incorrect use of **AccuCast™ 77**.

Raked joints are not permitted. Be sure to cover the top courses at the end of each workday to prevent collection of water in cores. If necessary, only use mild acid for cleanup. Do not use high pressure cleaning methods.

## TECHNICAL NOTE:

Flashing and weep hole design details are available upon request.

Efflorescence occurs when excess calcium salts become soluble again from moisture in the environment around the concrete or masonry unit. External sources of moisture can be humidity, rainfall, condensation, or snow etc. When these salts become soluble, they migrate to the surface during the evaporation process, consequently, staining the surface. **AccuCast™ 77**, as mentioned earlier, effectively reduces moisture from penetrating the surface and may be helpful in stopping salts from becoming soluble and migrating to the surface. It is important to point out though, that the addition of **AccuCast™ 77** alone, will not guarantee the control of efflorescence.

## PACKAGING:

55-gallon drums, 275-gallon totes, and bulk delivery.

## SHELF LIFE:

12 months

*Premiere Concrete Admixtures warrants its products to be free from defects in material and manufacture. There are no other warranties by Premiere Concrete Admixtures of any nature whatsoever, expressed or implied. This information is based on data and knowledge believed to be true and accurate at time of publication and is offered as a resource for the users of our products. Premiere Concrete Admixtures assumes no liability in the use of this information and does not warranty the results obtained for any application. Premiere Concrete Admixtures shall not be liable for damages of any sort, the use or results of this product and shall not be responsible for conditions outside its control, including but not limited to, other materials, design, inspection, workmanship and field conditions. No statement, recommendation, or other information is intended to infringe on any patent or copyright held by others.*

