


FLO™ - CF



Admixture for Cellular and Pre-Foamed Lightweight Concrete

DESCRIPTION

FLO-CF is a concentrated solution of selected surfactants. When used with a Foam Generator and a suitable water supply, **FLO-CF** produces a consistent pre-foam that is stable under alkaline conditions and suitable for use in the production of foamed concrete. Foamed concrete is the industry term used for the product produced by the controlled addition of a pre-foam to a cement grout or sand/cement mortar. A range of densities can be produced, typically from 20 to 100 lb/ft³. Foamed concrete is lightweight and highly mobile, able to flow for long distances under its own hydraulic head, and is an ideal material for uses such as void filling, roof screeds and trench reinstatement.

APPLICATIONS

Typical applications for foamed concrete include but are not limited to:

- Controlled low strength materials
- Trench filling for permanent, non-sink reinstatement
- Elimination of fire risks, health hazards and control of progressive collapse in areas such as underground fuel tanks, below railway platforms, old mine workings, sinkholes, industrial remediation, nuclear decommissioning and abandoned sewers
- As a lightweight thermal insulating material for roof screeds, suspended floors and basements
- As a semi-structural support in embankments, bridge abutments, tunnels and arches

SPECIFICATIONS

Conforms to ASTM C 869 "Standard Specification For Foaming Agents Used In Making Preformed Foam For Cellular Concrete"

ADVANTAGES

- Produces a consistent, stable pre-foam when used with a Foam Generator
- Easily controlled addition of pre-foam to pre-batched mortar allows close control of finished density
- Expensive blending equipment is not required as mixing can be carried out in the drum of a ready mix truck
- Produces a highly mobile foamed concrete which is easily placed without compaction
- Foamed concrete retains its volume and does not sink during or after hardening

COMPATIBILITY

FLO-CF is compatible with all types of Portland cement, class C and F fly ash, silica fume, calcium chloride, fibers and approved air entraining, accelerating, retarding, superplasticizing, and water-reducing admixtures. **FLO-CF** can be used in white, colored, and architectural concrete. For best results, each admixture must be dispensed separately into the concrete mix.

DOSAGE

The dosage of **FLO-CF** depends upon the original starting materials and the desired final density of the foamed concrete. Typical dosages are in the range of 16 to 64 ounces per cubic yard of finished foamed concrete over a density range of 20 to 100 lb/ft³. The optimum dosage of **FLO-CF** to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. Dosages outside the typical range suggested on this data sheet may be used if necessary and suitable to meet particular mix requirements. Contact your local Premiere technical service representative for advice in these cases.

TECHNICAL NOTE

FLO-CF does not contain calcium chloride or any chloridebased components. It will not promote or contribute to corrosion of reinforcing steel in concrete.



PREMIERE CONCRETE SOLUTIONS

P.O. Box 157 • 508 Cedar Street • Pioneer, Ohio 43354

Phone: (800) 503-3418 • Fax: (419) 737-9400

Email: support@premiereconcretesolutions.com

Website: www.bearcoat.net

FLO™ - CF

INSTRUCTIONS FOR USE

A pre-foam is produced by feeding **FLO-CF** through a Foam Generator. Either a water or air foam generator may be used. No pre-dilution is required with water foam generators. Air foam generators require a pre-dilution ratio of 1 part **FLO-CF** to 15-35 times water. Foam generators should be fitted with a proportional feeder unit set to correctly dispense **FLO-CF**.

Only potable water should be used for the pre-foam. Concrete wash water or water from other sources containing high levels of calcium ions should not be used. Different foaming equipment will have varied results. Test mixes should always be performed with equipment to be used on project in order to ensure accuracy.

LIMITATIONS

Trials should be made using relevant materials and conditions in order to determine the optimum mix design and admixture dosage to meet specific requirements. Compressive strength is proportional to its density and also to the cement content of the original mortar. A number of factors, such as water to cement ratio and the materials used, can affect the unit weight and compressive strength.

FLO-CF is not intended for direct addition to the mortar and use in this manner will not produce foamed systems. **FLO-CF** may not be suitable for use with certain sands, in particular coarse sands. Sands containing a significant amount of particles greater than a #16 sieve should be avoided. Pre-foam should not be made using concrete wash water or water from other sources containing high levels of calcium ions.



Premiere Concrete Solutions warrants its products to be free of manufacturing defects and that they will meet Premiere Concrete Solutions current published physical properties when applied in accordance with Premiere Concrete Solutions directions and tested in accordance with ASTM and Premiere Concrete Solutions standards. Premiere Concrete Solution makes no warranty or guarantee, express or implied, including warranties of fitness for a particular purpose or merchantability, respecting its products, and Premiere Concrete Solutions shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. Our liability shall be limited to replacement of, or refund of an amount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. In no case shall we be liable for consequential or special damages. Even if we have been advised of the possibility of such damages. The foregoing warranties are in lieu of all other warranties, guarantees, co-conditions and representations, either expressed or implied, whether arising under any statute. Common Law, usage or trade, course of dealing or otherwise, including, but not limited to, the implied warranties of merchantability or fitness for a particular purpose. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith.

© 2004 Premiere Concrete Solutions

YIELD

Unless extremely tight control is exercised, the density of a foamed concrete is likely to vary by ± 20 lb/yd³. This variability should be considered when estimating the possible volume of material required. Some factors may affect density and yield. Losses will not always occur but the possibility should be considered. Possible causes of loss include:

- Transportation of foamed concrete over long distances, such as when pre-foam is added at a batch plant instead of on-site
- Delays in placing and pumping
- Foamed concrete placed against a dry substrate causing foam collapse due to the suction of water out of the foamed concrete. If this occurs, wet substrate before placing the foamed concrete to reduce the likelihood of the problem.

STORAGE

FLO-CF may freeze at temperatures below 32°F (0°C). Although freezing does not harm **FLO-CF**, precautions should be taken to protect it from freezing. If it should happen to freeze, thaw and reconstitute with mechanical agitation. Do Not Use Pressurized Air For Agitation.

PACKAGING

5-gallon pails, 55-gallon drums, and 275-gallon tote tanks

SHELF LIFE

12 Months

This Product is formulated and labeled for Industrial and Commercial Use only. For best results and safest usage, user is specifically directed to consult the current material safety data sheet and package label for this product.