

OptiFlo® 50

Water-Reducing Admixture for Concrete

PRODUCT INFORMATION

PACKAGING

Packaged in 55 gallon drums, 275 gallon totes, and in bulk.

SHELF LIFE

2 years in original unopened container.

STORAGE

OptiFlo® 50 may freeze at temperatures below 35°F (2°C). Although freezing does not harm **OptiFlo® 50**, precautions should be taken to protect it from freezing. If it should happen to freeze, thaw and reconstitute with mechanical agitation. **Do not use pressurized air for agitation.**

SPECIFICATIONS/COMPLIANCES

ASTM C494 Type A and D
AASHTO M 194 Type A and D

DESCRIPTION

OptiFlo® 50 is a ready to use liquid chemical admixture formulated from a blend of high-quality lignosulfonate and other proprietary ingredients designed to enhance the performance of plastic and hardened concrete. **OptiFlo® 50** is manufactured under rigid quality control measures to provide uniform, reliable results.

OptiFlo® 50 is designed to facilitate the placing and finishing of concrete, and is recommended for mixes where reduced water content and improved cement performance is desirable.

PERFORMANCE BENEFITS

- Reduces w/cm ratio
- Increases compressive/ flexural strengths
- Improves finishability
- Improves workability
- Uniform set control
- Reduces cracking and shrinkage

DOSAGE RATES AND DIRECTIONS FOR USE

Important: Recommended dosage applies when no additional water reducers are included in the mix design. When using water reducing admixtures in combination, the dosage will vary to meet ASTM standards. Consult your local technical sales rep for those combination dosages.

By varying the dosage rate, **OptiFlo® 50** can be used as a low-range water reducer, or a water reducing and retarding admixture.

Recommended Dosage OptiFlo® 50		
Water Reducing	3 - 5 oz/cwt	195 – 325 mL/100kg
Water Reducing and Retarding	5 - 8 oz/cwt	325 – 520 mL/100kg
<i>Dosage is per hundred-weight of cementitious material.</i>		

For best results, each admixture must be batched at separate intervals with the initial or final batch water, and should not come in direct contact with any other admixture until they are mixed in the concrete batch. Admixtures should not come in contact with any dry cementitious material.

TECHNICAL NOTES

OptiFlo® 50 is compatible with Portland cements, blended cements, class C and F fly ash, slag cements, silica fume, calcium chloride, and fibers. **OptiFlo® 50** can be used in all white, colored, and architectural concrete.

PRECAUTIONS/LIMITATIONS

This product does not contain calcium chloride or chloride containing compounds, and any chloride ions present are in trace amounts resulting from municipal water used during the manufacturing process.

This product is compatible with most other admixtures when added to the mix separately. Always conduct trial batches, prior to job applications, to confirm compatibility and to verify mix results. Contact your technical sales representative before dosing outside of recommended ranges or for assistance with specialty applications.

In all cases, consult the safety data sheet prior to use.

Premiere Concrete Admixtures (herein PCA) warrants its products to be free from defects in material and manufacture. There are no other warranties by PCA of any nature whatsoever, expressed or implied. This information is based on data and knowledge believed to be true and accurate at time of publication and is offered as a resource for the users of our products. PCA shall not be liable in the use of this information and does not warranty the results obtained for any application. PCA shall not be liable for damages of any sort, the use or results of this product and shall not be responsible for conditions outside its control, including but not limited to, other materials, design, inspection, workmanship and field conditions. No statement, recommendation, or other information is intended to infringe on any patent or copyright held by others.