

# OptiFlo® 100R

## Set Retarding Water-Reducing Admixture for Concrete

### PRODUCT INFORMATION

#### PACKAGING

Packaged in 55 gallon drums, 275 gallon totes, and in bulk.

#### SHELF LIFE

2 years in original unopened container.

#### STORAGE

**OptiFlo® 100R** may freeze at temperatures below 35°F (2°C).

Although freezing does not harm

**OptiFlo® 100R**, precautions should be taken to protect it from freezing. If it should happen to freeze, thaw and reconstitute with mechanical agitation. **Do not use pressurized air for agitation.**

#### SPECIFICATIONS/COMPLIANCES

ASTM C494 Type B and D

AASHTO M 194 Type B and D

### DESCRIPTION

**OptiFlo® 100R** is a set retarding, water-reducing admixture for concrete. It provides uniform set characteristics for hot weather applications by controlling hydration.

This product is a valuable tool to control both plastic and hardened concrete properties. Placing and finishing crews benefit from longer working times when using **OptiFlo® 100R**.

### PERFORMANCE BENEFITS

- Slows rate of set in hot weather concrete
- Maintains slump life during extended mixing and transportation times
- Reduces w/cm ratio
- Increases compressive/ flexural strengths
- Increases density and durability
- Improves cementitious hydration and efficiency
- Reduces cracking and shrinkage
- Reduces segregation

### DOSAGE RATES AND DIRECTIONS FOR USE

**Important:** Recommended dosage applies when no additional water reducers are included in the mix design. When using water reducing admixtures in combination, the dosage will vary to meet ASTM standards. Consult your local technical sales rep for those combination dosages.

**OptiFlo® 100R** is recommended for use at a dosage rate of 2 to 8 oz/cwt of cementitious material. (130 to 520 mL/100 kg)

For best results, each admixture must be batched at separate intervals with the initial or final batch water, and should not come in direct contact with any other admixture until they are mixed in the concrete batch. Admixtures should not come in contact with any dry cementitious material.

### TECHNICAL NOTES

**OptiFlo® 100R** is compatible with Portland cements, Portland limestone cements, blended cements, class C and F fly ash, slag cements, silica fume, calcium chloride, and fibers. **OptiFlo® 100R** can be used in all white, colored, and architectural concrete.

---

## PRECAUTIONS/LIMITATIONS

This product does not contain calcium chloride or chloride containing compounds, and any chloride ions present are in trace amounts resulting from municipal water used during the manufacturing process.

This product is compatible with most other admixtures when added to the mix separately. Always conduct trial batches, prior to job applications, to confirm compatibility and to verify mix results. Contact your technical sales representative before dosing outside of recommended ranges or for assistance with specialty applications.

In all cases, consult the safety data sheet prior to use.

---

Premiere Concrete Admixtures (herein PCA) warrants its products to be free from defects in material and manufacture. There are no other warranties by PCA of any nature whatsoever, expressed or implied. This information is based on data and knowledge believed to be true and accurate at time of publication and is offered as a resource for the users of our products. PCA shall not be liable in the use of this information and does not warranty the results obtained for any application. PCA shall not be liable for damages of any sort, the use or results of this product and shall not be responsible for conditions outside its control, including but not limited to, other materials, design, inspection, workmanship and field conditions. No statement, recommendation, or other information is intended to infringe on any patent or copyright held by others.